

Product properties				
Format [mm]		570 x 95 x 13	1882* x 190 x 15	2200* x 185 x 15
Top layer		ca. 3,6 mm	ca. 4,0 mm	ca. 3,6 mm
Packaging	Pack:	16 Elements	8 Elements	8 Elements
	m ² /kg	0,866 / 4,32	2,861 / 23,464	3,663 / 26,048
	Pallet:	36 Packs	32 Packs	32 Packs
		31,176 / 155,52	91,546 / 750,848	117,22 / 833,536
*1 joint length permitted per package			Notes	- cleaning and maintenance see instructions - technical changes reserved
Guarantee (according to Parador guarantee conditions)		25 years (domestic area)		

Product labelling			Tolerances (EN 13489)	
        			Admissible difference in length (± 0.1 %)	± 0,05%
			Admissible difference in width (± 0.2 mm)	± 0,1 mm
			Squareness of the element (≤ 0.2 %)	≤ 0,05 %
			Longitudinal curvature along the element (≤ 0.1 %)	≤ 0,05 %
			Transverse curvature across the width (≤ 0.2 %)	≤ 0,08 %
			Height differences of elements (≤ 0.2 mm)	≤ 0,18 mm
			Moisture content at the time of first delivery (5-9%)	6 – 8 %

Classification general product features			
		Test method	Rating
	Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chairmat
	Effect of a furniture leg	EN ISO 16581	No visible changes
	Thermal resistance Suitable for installation over underfloor heating when using an appropriate underlay and moisture barrier.	EN ISO 10456	Thickness: 13mm 0,087 m ² K/W Thickness: 15mm 0,100 m ² K/W
	Formaldehyde (E1 = 0,1 ppm)	EN 16516	≤ 0,05 ppm
	Acoustical - Impact noise reduction	ISO 717-2	Thickness: 13mm - only suitable for all-over adhesion Thickness: 15mm 18 dB (with Akustik-Protect 100)
	Disposal	EAK-Code-number 20 01 38	

Classification surface characteristics				
		Test method	Rating	
	Slip resistance	EN 13893	Natural oiled plus μ ≥ 0,49	Lacquer μ ≥ 0,47
		CEN/TS 15676	99 (USRV)	29 SRT (SRV wet) 51 SRT (SRV dry)
	Reaction to fire, click-installation as a floating floor	EN 13501-1	D _f s1	
	Reaction to fire, installation by all-over adhesion	EN 13501-1	D _f s1	
	Chemical resistance	EN 13442:2023 Annex B	Category 5	
	Bond strength / Cross cutting test	ISO 2409	n.n.	Category 0
	Slip resistance, inclined plane	EN 16165, Annex B	R 10	R 9

Changed:	QMB	File name:	PA TDS Parkett Selected EN 20240101
Date:	01.05.2013	Latest update at	https://parador.de/en/pcms/downloads/downloadfile/file_id/1549/
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.01.2024

Free sorting according to EN 13489				
Assortment:	Selected			
Characteristics according to EN 1310:	Upper side of the plank			
Format:	570x95x13mm	1882x190x15mm	2200x185x15mm	
Type of wood:	Oak			
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE	Quercus spp. / QCXE	Quercus petraea Liebl., Quercus robur L. / QCXE	
Shortcut / sorting (internal):	ER-TT3-EI	ER-TT8-EI	ER-LH-EI	
	Version 7 2022	Version 4 2015	Version 4 2021	
Grade:	Living	Classic	Natur	Rustikal
Sound sapwood	permitted		not permitted	
Knot (intergrown)	permitted: up to 30 mm	permitted	permitted: up to 30 mm	permitted: up to 80 mm
Falling out knot	permitted: up to 10 mm	permitted	permitted: up to 15 mm	permitted: up to 60 mm
Pinknots	permitted			permitted: cluster of knots
Filling	permitted			
Slight cracks / hairline cracks	permitted			
Bark pocket	not permitted			permitted
Lightning cracks	permitted			
Slope of grain	no criterion			
Healthy heart	-	permitted	not permitted: coretube	permitted
Medullary ray	permitted			
Discoloration, colour variation	permitted: all colours		permitted: slight colour variations	permitted: all colours
White streaks	permitted			
Pilling sticks marking	not permitted			
Biodeterioration (EN 1311)	not permitted			
Non-visible parts				
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.				
Comment				
Maximum 3% of planks are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.				

Changed:	QMB	File name:	PA_TDS_Parkett_Selected_Anhang_EN_20240101	
Date:	01.03.2013	Update:	https://parador.de/en/pcms/downloads/downloadfile/file_id/1549/	
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.01.2024	Page 1 of 1